

USSN 09/943,925

AMENDMENTS TO THE CLAIMS:

1.(currently amended)(third amendment) An article which is a film, sheet, extruded profile, fiber, ~~coated article, rotational molded article, or blow molded article~~ produced from, or an article coated with, a composition comprising a hydrogenated block copolymer, wherein the hydrogenated block copolymer comprises at least two distinct blocks of hydrogenated vinyl aromatic polymer, and at least one block of hydrogenated conjugated diene polymer, wherein the copolymer is further characterized by:

a) a weight ratio of hydrogenated conjugated diene polymer block to hydrogenated vinyl aromatic polymer block of 40:60 or less;

b) a total weight average molecular weight (M_w) of from 30,000 to 150,000, wherein each hydrogenated vinyl aromatic polymer block (A) has a M_w of from 6,000 to 60,000 and each hydrogenated conjugated diene polymer block (B) has a M_w of from 3,000 to 30,000; and

c) a hydrogenation level such that each hydrogenated vinyl aromatic polymer block has a hydrogenation level of greater than 90 percent and each hydrogenated conjugated diene polymer block has a hydrogenation level of greater than 95 percent.

2.(original) The article of Claim 1 wherein the hydrogenated vinyl aromatic polymer block is selected from the group consisting of hydrogenated polystyrene, a hydrogenated alpha-methylstyrene polymer, a hydrogenated vinyltoluene, a hydrogenated copolymer of styrene and alpha-methylstyrene, and a hydrogenated copolymer of styrene and vinyl toluene; and the hydrogenated conjugated diene polymer block is selected from the group consisting of hydrogenated polybutadiene, hydrogenated polyisoprene, and a hydrogenated copolymer of butadiene and isoprene.

3. (original) The article of Claim 1 wherein the composition additionally comprises at least one additional polymer.

4. (original) The article of Claim 3 wherein the other polymer is selected from the group consisting of hydrogenated vinyl aromatic homopolymers, other hydrogenated vinyl aromatic/conjugated diene block copolymers, thermoplastic

USSN 09/943,925

polyurethanes, polycarbonates (PC), polyamides, polyethers, poly/vinyl chloride polymers, poly/vinylidene chloride polymers, polyesters, polymers that contain lactic acid residuals, partially or non-hydrogenated vinyl aromatic/conjugated diene block polymers, a styrenic polymer, acrylonitrile-butadiene-styrene (ABS) copolymers, styrene-acrylonitrile copolymers (SAN), ABS/PC polymers, polyethylene terephthalate, epoxy resins, ethylene vinyl alcohol copolymers, ethylene acrylic acid copolymers, polyolefin carbon monoxide interpolymers, chlorinated polyethylene, cyclic olefin copolymers (COC's), and olefin homopolymers and copolymers.

5. (original) The article of Claim 4 wherein the additional polymer is selected from the group consisting of a polyolefin, ethylene/styrene interpolymers, a partially or non-hydrogenated vinyl aromatic/conjugated diene block copolymer, a styrenic polymer, hydrogenated polystyrene, an other hydrogenated vinyl aromatic/conjugated diene block copolymer and a cyclic olefin (co) polymer derived from monomers selected from the following group: substituted and unsubstituted norbornenes, dicyclopentadienes, dihydrodicyclopentadienes, trimers of cyclopentadiene, tetracyclododecenes, hexacycloheptadecenes, ethylidenyl norbornenes and vinylnorbornenes.

6. (original) The article of Claim 1, wherein the hydrogenated block copolymer is present in an amount of from 0.5 to 99.5 weight percent, based on the total weight of the composition.

7. (original) The article of Claim 1 wherein the composition additionally comprises a compatibilizer.

8. cancelled

9. (previously amended) The article of Claim 1 which is a capacitor film, a membrane switch, blister packaging, a UV protection film, biaxially oriented film, uniaxially oriented film, weatherable film or sheet, label, release liner, window film for envelope or box, medical packaging film, a tray, a liquid crystal panel, a cap layer for polyolefin sheet, a key pad, a flat panel display, optical display panel, a window blind, window blind wand, tubing, pipe, construction siding, roofing product, window trim, glazing, ceiling panel, solar collector, flat panel display,

44653A

-3-

USSN 09/943,925

thermoformed container, wind screen, bug deflector, sun roof, basketball backboard, cap layer for polyolefin sheet, electronic optical fiber, fiber glass, fiber reinforcement, filter media, textile, nonwoven article, yarn, a bottle, a toy, an injection blow molded article, container, light globe, storage tank, furniture, whirlpool tub, boat, camper top, advertising display sign, rack, or mannequin.

10. (previously amended) A composition comprising:

I) at least one hydrogenated block copolymer which comprises at least two distinct blocks of hydrogenated vinyl aromatic polymer, and at least one block of hydrogenated conjugated diene polymer, wherein the copolymer is further characterized by:

a) a weight ratio of hydrogenated conjugated diene polymer block to hydrogenated vinyl aromatic polymer block of 40:60 or less;

b) a total weight average molecular weight M_w of from 30,000 to 150,000, wherein each hydrogenated vinyl aromatic polymer block (A) has a M_w of from 6,000 to 60,000 and each hydrogenated conjugated diene polymer block (B) has a M_w of from 3,000 to 30,000; and

c) a hydrogenation level such that each hydrogenated vinyl aromatic polymer block has a hydrogenation level of greater than 90 percent and each hydrogenated conjugated diene polymer block has a hydrogenation level of greater than 95 percent, and

II) at least one additional polymer.

11. (original) The composition of Claim 10 wherein the additional polymer is selected from the group consisting of hydrogenated vinyl aromatic homopolymers, other hydrogenated vinyl aromatic/conjugated diene block copolymers, thermoplastic polyurethanes, polycarbonates (PC), polyamides, polyethers, poly/vinyl chloride polymers, poly/vinylidene chloride polymers, polyesters, polymers that contain lactic acid residuals, partially or non-hydrogenated vinyl aromatic/conjugated diene block copolymers, styrenic polymers, acrylonitrile-butadiene-styrene (ABS) copolymers, styrene-acrylonitrile copolymers (SAN), ABS/PC polymers, polyethylene

USSN 09/943,925

terephthalate, epoxy resins, ethylene vinyl alcohol copolymers, ethylene acrylic acid copolymers, polyolefin carbon monoxide interpolymers, chlorinated polyethylene, cyclic olefin copolymers (COC's), and olefin homopolymers and copolymers.

12. (original) The composition of Claim 11 wherein the additional polymer is selected from the group consisting of a polyolefin, ethylene/styrene interpolymers, a partially or non-hydrogenated vinyl aromatic/conjugated diene block copolymer, a styrenic polymer, hydrogenated polystyrene, an other hydrogenated vinyl aromatic/conjugated diene block copolymer and a cyclic olefin (co) polymer derived from monomers selected from the following group: substituted and unsubstituted norbornenes, dicyclopentadienes, dihydrodicyclopentadienes, trimers of cyclopentadiene, tetracyclododecenes, hexacycloheptadecenes, ethylidenyl norbornenes and vinylnorbornenes.

13. (original) The composition of Claim 10, wherein the hydrogenated block copolymer is present in an amount of from 0.5 to 99.5 weight percent, based on the total weight of the composition.

14. (original) The composition of Claim 10 wherein the composition additionally comprises a compatibilizer.

Claims 15-21 (cancelled).